

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Currently Amended): A separator for batteries comprising a multi-component composite membrane, wherein the multi-component composite membrane comprises ~~comprising~~ active layers and support layers, wherein a support layer is located between active layers, wherein the active layers have pores having a pore size and a pore distribution, and wherein the support layer has pores having a different pore size and a different pore distribution.
2. (Currently Amended): The separator for batteries as claimed in ~~multi-component composite membrane according to~~ claim 1, wherein a component of the a support layer is at least one polymer selected from the group consisting of high density polyethylene, low density polyethylene, linear low density polyethylene, polypropylene, crystalline polypropylene, polyethylene-propylene copolymer, polyethylene-butylene copolymer, polyethylene-hexene copolymer, polyethylene-octene copolymer, polystyrene-butylene-styrene copolymer, polystyrene-ethylene-butylene-styrene copolymer, polystyrene, polyphenylene oxide, polysulfone, polycarbonate, polyester, polyamide, polyurethane, polyacrylate, polyvinylidene ~~chloride~~ chloride, polyvinylidene fluoride, polysiloxane, polyolefin, ionomer, polymethylpentene, and hydrogenated oligocyclopentadiene (HOCP), and a derivative thereof.
3. (Currently Amended): The separator for batteries as claimed in ~~multi-component composite membrane according to~~ claim 2, wherein the crystalline polypropylene has one or more physical properties selected from the group consisting of a density of 0.905 g/cc or more, a melting point of 164 °C or higher, a crystallization

temperature of 125 °C or higher, a crystallinity of 50% or greater, an isotacticity of 96% or greater, and an atactic fraction of 5% or less.

4. (Currently Amended): The separator for batteries as claimed in multi-
~~component composite membrane according to~~ claim 1, wherein a the pore size of a the
support layer ranges from 0.001 to 10 μm .

5. (Currently Amended): The separator for batteries as claimed in multi-
~~component composite membrane according to~~ claim 1, wherein a thickness of a the
support layer ranges from 1 to 50 μm .

6. (Currently Amended) The separator for batteries as claimed in multi-
~~component composite membrane according to~~ claim 1, wherein a component of the
active layers is one or more polymers selected from the group consisting of
polyethylene, polypropylene, polyvinylidene fluoride, polyvinylidene fluoride-
hexafluoropropylene copolymer, polyethylene oxide, polypropylene oxide,
polybutylene oxide, polyurethane, polyacrylonitrile, polyacrylate, polyacrylic acid,
polyamide, polyacrylamide, polyvinylacetate, polyvinylpyrrolidone, polytetraethylene
glycol diacrylate, polysulfone, polyphenylene oxide, polycarbonate, polyester,
polyvinylidene chloride, polysiloxane, and polyolefin ionomer, and a derivative thereof.

7. (Currently Amended): The separator for batteries as claimed in multi-
~~component composite membrane according to~~ claim 6, wherein a solvent for the
component of the active layers is one or more solvents selected from the group
consisting of 1-methyl-2-pyrrolidone (NMP), acetone, ethanol, n-propanol, n-butanol, n-
hexane, cyclohexanol, acetic acid, ethyl acetate, diethyl ether, dimethyl formamide
(DMF), dimethylacetamide (DMAc), dioxane, tetrahydrofuran (THF), dimethyl
sulfoxide (DMSO), cyclohexane, benzene, toluene, xylene, and water, and a ~~mixture~~
mixture thereof.

8. (Currently Amended): The separator for batteries as claimed in ~~multi-~~
~~component composite membrane according to claim 1~~, wherein ~~a~~ the pore size of ~~an~~ at least one active layer is equal to or less than 10 μm .
9. (Currently Amended): The separator for batteries as claimed in ~~multi-~~
~~component composite membrane according to claim 1~~, wherein a thickness of ~~an~~ at least one active layer ranges from 0.01 to 20 μm .
10. (Currently Amended): The separator for batteries as claimed in ~~multi-~~
~~component composite membrane according to claim 1~~, wherein air permeability of the multi-component composite membrane is equal to or less than 7,000 sec/100 cc.
11. (Currently Amended): The separator for batteries as claimed in ~~multi-~~
~~component composite membrane according to claim 1~~, wherein a wet-out rate of the multi-component composite membrane is equal to or less than 30 seconds.
12. (Currently Amended): The separator for batteries as claimed in ~~multi-~~
~~component composite membrane according to claim 1~~, wherein the multi-component composite membrane comprises two or more active layers and one or more support layers, and the composite membrane has a structure of triple or multiple layers.
13. (Currently Amended): The separator for batteries as claimed in ~~multi-~~
~~component composite membrane according to claim 2~~, wherein the support layer is blended or laminated with at least one polymer.
14. (Currently Amended): The separator for batteries as claimed in ~~multi-~~
~~component composite membrane according to claim 1~~, wherein the multi-component composite membrane is used for water treatment, hemodialysis, enzyme purification, patches for drug delivery, gas separation, pervaporation, reverse osmosis, or electrolysis separation.

Claim 15. (Cancelled)

16. (Currently Amended): A rechargeable lithium ion battery or a rechargeable lithium ion polymer battery comprising ~~the~~ a multi-component composite membrane of ~~claim 1~~ as a separator, wherein the multi-component composite membrane comprises active layers and support layers, wherein a support layer is located between active layers, wherein the active layers have pores having a pore size and a pore distribution, and wherein the support layer has pores having a different pore size and a different pore distribution.

17. (Previously Presented): A preparation method of a multi-component composite membrane comprising steps of:

- a) preparing a precursor film by injection of a polymer, which is used, for a support layer into an extruder;
- b) annealing the precursor film at a temperature less than a melting point of the polymer;
- c) coating both surfaces of the precursor film with a polymer solution, which is used for an active layer;
- d) drying the coated precursor film;
- e) low temperature-stretching the dried precursor film at a temperature less than room temperature;
- f) high temperature-stretching the low temperature-stretched precursor film at a temperature less than the melting point of the polymer; and
- g) heat-setting the high temperature-stretched precursor film under tension at a temperature less than the melting point of the polymer.

18. (Previously Presented): The preparation method according to claim 17, wherein the polymer solution of step c) is coated on both sides of the precursor film by dip-coating.

19. (Previously Presented): The preparation method according to claim 17, wherein a concentration of the polymer solution of step c) is equal to or greater than 0.01 wt%.

20. (Previously Presented): The preparation method according to claim 17, wherein the drying of step d) is performed at a relative humidity ranging from 1 to 100%.
21. (Previously Presented): The preparation method according to claim 17, wherein the drying of step d) is performed under saturated vapor pressure.
22. (Previously Presented): The preparation method according to claim 17, wherein the drying of step d) is performed under a gas atmosphere selected from the group consisting of nitrogen, oxygen, carbon dioxide, and air atmosphere.
23. (Previously Presented): The preparation method according to claim 17, wherein an active layer having a thickness in the range of 0.1 to 20 μm is formed through the coating and drying of steps c) and d).
24. (Previously Presented): The preparation method according to claim 17, which further comprises the step of applying ion beams to either or both surfaces of the annealed precursor film with reactive gas between the steps b) and c).
25. (Previously Presented): The preparation method according to claim 24, wherein the ion beam irradiation is performed by activation of electrons and a gas selected from the group consisting of hydrogen, helium, oxygen, nitrogen, carbon dioxide, air, fluorine, neon, argon, krypton, N_2O , and a mixture thereof such that the gas has an energy ranging from 0.01 to 10^6 keV; and irradiating the surface of the precursor film with the ion beams.
26. (Previously Presented): The preparation method according to claim 24, wherein the ion beam irradiation amount ranges from 10^5 to 10^{20} ions/ cm^2 .
27. (Currently Amended): The preparation method according to claim 24, wherein the ~~iron~~ ion beam irradiation is performed under a gas atmosphere selected from the group consisting of helium, hydrogen, nitrogen, ammonia, carbon monoxide,

carbon dioxide, chlorofluoro methane, methane, and N₂O atmospheres, and ~~a mixture~~ mixtures thereof.

28. (Original): The preparation method according to claim 27, wherein the flow rate of the reactive gas ranges from 0.5 to 20 ml/minute.

29. (Canceled).

30. (Previously Presented): The preparation method according to claim 24, wherein the ion beam irradiation is performed under a vacuum ranging from 10⁻¹ to 10⁻⁶ torr.

31. (Currently Amended): The separator for batteries as claimed in multi-
~~component composite membrane according to claim 1~~, wherein the pores of the support layer are formed by a stretching process after orienting a polymer crystalline region in a certain direction and the pores of ~~the~~ at least one active layer are formed by a stretching process after forming a polymer film through phase-inversion.

32. (Currently Amended): The separator for batteries as claimed in multi-
~~component composite membrane according to claim 1~~, wherein ~~an~~ at least one active layer has pores having a pore size equal to or less than 10 μm.

33. (Previously Presented): A preparation method of a multi-component composite membrane comprising steps of:

- a) annealing a precursor film comprising a polymer at a temperature less than a melting point of the polymer;
- b) coating both surfaces of the precursor film with a polymer solution, which is used for an active layer;
- c) drying the coated precursor film;
- d) low temperature-stretching the dried precursor film at a temperature less than room temperature;

- e) high temperature-stretching the low temperature-stretched precursor film at a temperature less than the melting point of the polymer; and
- f) heat-setting the high temperature-stretched precursor film under tension at a temperature less than the melting point of the polymer.

34. (Previously Presented): The preparation method according to claim 33, wherein the polymer solution of step b) is coated on both sides of the precursor film by dip-coating.

35. (Previously Presented): The preparation method according to claim 33, which further comprises the step of applying ion beams to either or both surfaces of the annealed precursor film with reactive gas between the steps a) and b).

36. (Previously Presented): The preparation method according to claim 35, wherein the ion beam irradiation is performed by activation of electrons and a gas selected from the group consisting of hydrogen, helium, oxygen, nitrogen, carbon dioxide, air, fluorine, neon, argon, krypton, N₂O, and a mixture thereof such that the gas has an energy ranging from 0.01 to 10⁶ keV; and the surface of the precursor film with the ion beams.

Claims 37-46. (Cancelled)

47. (Previously Presented): The separator for batteries as claimed in multi-
~~component-composite membrane according to claim 1,~~ wherein the pores of the support layer are formed by a stretching process and the pores of ~~the~~ at least one active layer are formed by a stretching process after being formed by a phase-inversion.

48. (New): A separator for batteries comprising the multi-component composite membrane made by the preparation method of claim 17.

49. (New): A rechargeable lithium battery comprising the multi-component composite membrane made by the preparation method of claim 17 as a separator.

50. (New): A separator for batteries comprising the multi-component composite membrane made by the preparation method of claim 23.
51. (New): A rechargeable lithium battery comprising the multi-component composite membrane made by the preparation method of claim 23 as a separator.
52. (New): A separator for batteries comprising the multi-component composite membrane made by the preparation method of claim 24.
53. (New): A rechargeable lithium battery comprising the multi-component composite membrane made by the preparation method of claim 24 as a separator.
54. (New): A separator for batteries comprising the multi-component composite membrane made by the preparation method of claim 33.
55. (New): A rechargeable lithium battery comprising the multi-component composite membrane made by the preparation method of claim 33 as a separator.
56. (New): A separator for batteries comprising the multi-component composite membrane made by the preparation method of claim 35.
57. (New): A rechargeable lithium battery comprising the multi-component composite membrane made by the preparation method of claim 35 as a separator.
58. (New): A separator for batteries comprising the multi-component composite membrane made by the preparation method of claim 25.